

IAF-Radioökologie GmbH | Wilhelm-Rönsch-Straße 9 | 01454 Radeberg

DOYMA GmbH & Co  
Dichtungssysteme  
Brandschutzsysteme  
Industriestraße 43-57  
28876 Oyten



Radeberg, 2017-06-29

## Certificate

### *Determination of the Radon Diffusion Coefficient*

The radon diffusion coefficient  $D$  of the sealing system "Quadro-Sicura<sup>®</sup> Nova 2" as supplied by the client

DOYMA GmbH & Co  
Industriestraße 43-57  
28876 Oyten

has been experimentally determined by IAF-Radioökologie GmbH using a double chamber system. The results are provided in the following table.

Description of variables	Measured values
Diffusion coefficient $D$	$2.23 \cdot 10^{-10} \text{ m}^2/\text{s}$
Diffusion length $L_D$	10.30 mm
Material thickness $d$	60 mm
Area of the material $F$	491 $\text{cm}^2$
Test parameter $R = d/L_D$	5.83
Result	<b><math>R &gt; 3</math>, i.e., radon tight</b>

The result "radon tight" also applies to the sealing systems Quadro-Sicura<sup>®</sup> Nova 1, Quadro-Sicura<sup>®</sup> Nova 1-M, Quadro-Sicura<sup>®</sup> Nova 1/breit, Quadro-Sicura<sup>®</sup> Nova 2-M und Quadro-Sicura<sup>®</sup> Nova 2/breit.

A sealing system is rated "radon tight" if its thickness exceeds the radon diffusion length of the material at least by a factor 3. Otherwise the sealing system is rated "not radon tight". A "radon tight" sealing system is defined by a material which, when covering a radon-exhaling surface, reduces the exhalation rate by at least 95% compared to the bare surface.

Dr. rer. nat. habil. Hartmut Schulz

Managing Director